

Galaxy Minerals Singapore Pte Ltd.,


TECHNICAL DATA SHEET

PRODUCT : RIVER SAND

NO	TEST ITEM	METHOD	UNIT	LIMIT	RESULT
1	Particle Size Distribution	BS 12620 : 2022	%	Report	Refer to Annex
2	Fineness Modulus	BS 12620 : 2022	-	Report	2.90
3	Clay Content	BS 12620 : 2022	%	Report	0.22
4	Chloride	BS 12620 : 2022	mg/kg	Report	ND<8
5	Organic Impurities	BS 12620 : 2022	-	Report	Pass

ANALYSIS REPORT

Sieve Analysis and Fineness Modulus Table				
Sieve Aperture Size (mm)	Weight Retained (g)	Percentage of Weight Retained (%)	Cumulative Retained Percentage (%)	Passing Percentage (%)
4.750	1.42	0.28	0.28	99.72
2.360	25.73	5.04	5.32	94.68
1.180	112.79	22.1	27.42	72.58
0.600	207.3	40.61	68.03	31.97
0.300	113.9	22.31	90.34	9.66
0.150	45.73	8.96	99.30	0.70
Pan	3.57	0.70	100.00	0.00
Total	510.44			
Fineness Modulus = 2.90				



Galaxy Minerals Singapore Pte Ltd.,

